

Fasteners & Metals Interlaboratory Testing Program

Summary Report Cycle 1522, 4th Qtr 2025 (WT)

[About the Metals Program](#) [About CTS](#) [Key to Tables and Graphs](#)

Analysis

Test Group

Fasteners

[1201](#)

[Fastener Wedge Tensile \(10 degree\)](#)

ABOUT THE FASTENERS & METALS PROGRAM

Collaborative Testing Services operates and maintains the program for Fasteners and Metals as part of a series of Proficiency and Interlaboratory Testing Programs offered by CTS in cooperation with various associations for a wide range of industries. Personnel from the National Institute of Standards and Technology (formerly the National Bureau of Standards), Industrial Fasteners Institute (IFI), and the Naval Shipyard Laboratories provide technical guidance and advice to this program.

The purpose of the program is to give participating laboratories a means to compare periodically the level and uniformity of their testing with that of other laboratories in the industry. It also provides a realistic assessment of the state of fasteners and metals testing proficiency.

In each report, there is a summary of the statistics for the analysis and a graphical representation of the data for each test. Also shown are notes concerning specific laboratory results, as well as significant findings related to instrument types or other testing variations. Refer to the KEY TO TABLES AND GRAPHS for an explanation of terms and guidelines to interpreting the results.

ABOUT CTS

Founded in 1971, CTS is a privately-owned company that specializes in interlaboratory tests for a wide variety of industries including rubber, plastics, fasteners and metals, containerboard, paper, color, hemp, and wine as well as proficiency tests for forensic laboratories. All of the tests are designed to assist organizations in achieving and maintaining quality control objectives. Labs from the U.S., as well as more than 100 countries, currently participate in the CTS programs.

For further information contact:

COLLABORATIVE TESTING SERVICES, INC.
21331 Gentry Drive
Sterling, VA 20166


Phone: (571) 434-1925
FAX: (571)434-1937
e-mail: metals@cts-interlab.com
www.collaborativetesting.com
Office Hours: 8:00 a.m. - 4:30 p.m. ET

Key for Fasteners & Metals Program Web Summary Report

WebCode	- Assigned laboratory identification number(temporary)used to ensure lab confidentiality while permitting a lab to locate its data in the report published on the CTS website.
Lab Mean	- The average of the test results obtained by the participant.
Grand Mean	- The average of the LAB MEANS for all included participants. Laboratories flagged with an X or an M (see DATA FLAG column) are excluded from the GRAND MEAN.
Between-Lab Standard Deviation	- An indication of the precision of measurement between the laboratories. The greater the spread of the LAB MEANS about the GRAND MEAN, the larger the BETWEEN-LAB STANDARD DEVIATION (and vice versa).
Comparative Performance Value (CPV)	- An indication of how well a laboratory's results agree with the other participants. The CPV is a ratio indicating the number of standard deviations from the GRAND MEAN. $CPV = (LAB\ MEAN - GRAND\ MEAN) / BETWEEN-LAB\ STANDARD\ DEVIATION$. The closer a laboratory's COMPARATIVE PERFORMANCE VALUE is to zero, the more consistent its results are with the other participants' data (and vice versa).
Instr. Code	- A code indicating the manufacturer of the instrument used to perform the test (see separate INSTRUMENT CODE LIST for each test section).
Data Flag	- DATA FLAGS are assigned based on the simultaneous analysis of both samples tested. Refer to the following chart for an explanation of each symbol:

Data Flags

Data Flag Type	Statistically Included/Excluded	ACTION REQUIRED
*	INCLUDED	CAUTION - review testing procedure and monitor future results. Results fall outside the drawn 95% ellipse but within a 99% ellipse that is calculated but not drawn. Labs flagged with an * do not typically receive a specific note regarding the flag. If this error is repeated in future rounds, however, a lab may need to stop and review its testing procedures. The initial data flag is not cause for alarm.
X	EXCLUDED	STOP - immediate review of data and/or testing procedure is required (all tests except Chemical Analyses). Results fall outside the 99% ellipse. See the specific note following the data for more information on why the data are excluded. For Chemical Analyses see an additional Memo.
M	EXCLUDED	PROCEED - lab was unable to report data for at least one sample. However, a lab receiving two or more M flags for a test may need to stop and review its testing procedures.
Graph	<ul style="list-style-type: none"> - For each laboratory, the Lab Mean for the second sample (y-axis) is plotted against the Lab Mean for the first sample (x-axis) with each point representing a laboratory. The horizontal and vertical cross-hairs are the Grand Means for each sample. When 20 or more laboratories are included in the statistics, an ellipse is also drawn so that 95% of the time a randomly selected laboratory will be included inside the ellipse. Plotted data flags are explained above. Labs not receiving a data flag appear as points on the plot. 	



Fasteners and Metals Interlaboratory Testing Program

Analysis 1201


Fastener Wedge Tensile (10 degree) ASTM F606

Cycle 1522

4th Qtr 2025

(WT)

WebCode	Data Flag	Sample X13			Sample X14		
		Lab Mean	Diff. from Grand Mean	CPV	Lab Mean	Diff. from Grand Mean	CPV
236AUQ	X	135.76	-0.29	-0.18	137.85	5.13	4.44
2ZYRVV		138.11	2.06	1.29	134.05	1.34	1.16
3C4HWU		137.03	0.98	0.61	134.36	1.65	1.43
3HVPF3		134.33	-1.72	-1.08	133.00	0.29	0.25
43CHMA		136.07	0.01	0.01	131.67	-1.04	-0.90
4KBN3V		132.33	-3.72	-2.34	131.67	-1.04	-0.90
4L86ET		133.83	-2.22	-1.40	130.47	-2.24	-1.94
67AC7W		133.48	-2.57	-1.62	131.79	-0.92	-0.79
7436PP		136.90	0.85	0.53	134.19	1.48	1.28
7GPJHQ	X	51.43	-84.62	-53.19	50.33	-82.38	-71.28
7W3UBK		136.00	-0.05	-0.03	134.00	1.29	1.12
7XXDCL		137.63	1.58	0.99	132.70	-0.01	-0.01
8EUAZ9		135.63	-0.42	-0.26	132.63	-0.08	-0.07
8TVWDW		133.44	-2.61	-1.64	131.50	-1.21	-1.05
8Y3MJ9		137.67	1.61	1.01	132.67	-0.04	-0.04
9AJK7R		134.77	-1.29	-0.81	132.30	-0.41	-0.36
9GDBAJ		137.43	1.38	0.87	133.90	1.19	1.03
A2ZMT6		135.19	-0.87	-0.54	131.94	-0.77	-0.66
ANCJC8		137.66	1.61	1.01	133.98	1.26	1.09
CARVCL		137.00	0.95	0.59	133.67	0.96	0.83
CHV7CW		137.18	1.12	0.71	131.71	-1.00	-0.87
DZWEZM	*	134.40	-1.65	-1.04	134.20	1.49	1.29
E67QL3		135.73	-0.32	-0.20	131.97	-0.74	-0.64
EK3UBM		133.48	-2.57	-1.61	130.25	-2.47	-2.13
EY2Z6H		137.33	1.28	0.80	133.53	0.82	0.71
FDT6ZR		135.83	-0.22	-0.14	133.00	0.29	0.25
GUDCDG		135.21	-0.85	-0.53	131.37	-1.34	-1.16
J3YDPV		136.60	0.55	0.34	133.33	0.62	0.54
LN489		137.17	1.11	0.70	133.00	0.29	0.25
M3VH7G		135.93	-0.12	-0.08	131.80	-0.91	-0.79
MA8VRT		136.79	0.73	0.46	132.70	-0.01	-0.01
MT629Z		135.93	-0.12	-0.08	131.60	-1.11	-0.96
MTPXHE		138.56	2.50	1.57	134.69	1.98	1.71
N6W398		136.77	0.71	0.45	133.33	0.62	0.54
PLEBYA		136.80	0.75	0.47	133.23	0.52	0.45
QREAM4		134.67	-1.39	-0.87	130.63	-2.08	-1.80
RCFPJL		134.70	-1.35	-0.85	130.83	-1.88	-1.63
RQJ2Z7		134.67	-1.39	-0.87	133.23	0.52	0.45
T2VPHH	X	134.19	-1.86	-1.17	135.54	2.83	2.45
T6XJKU		135.00	-1.05	-0.66	132.43	-0.28	-0.24
TWFE6E		135.50	-0.55	-0.35	132.33	-0.38	-0.33
UEXNRZ		136.43	0.38	0.24	132.33	-0.38	-0.33
V6NGP7		136.30	0.25	0.15	131.73	-0.98	-0.85
VFRPE4		135.20	-0.85	-0.54	133.17	0.46	0.39
VH2JB4	X	137.36	1.31	0.82	138.31	5.60	4.85
VP3RZ6		134.90	-1.15	-0.73	133.13	0.42	0.37
VPVVXK		136.23	0.18	0.11	132.86	0.15	0.13



Fasteners and Metals Interlaboratory Testing Program

Analysis 1201

Fastener Wedge Tensile (10 degree)
ASTM F606

Cycle 1522

4th Qtr 2025

(WT)

WebCode	Data Flag	Sample X13			Sample X14		
		Lab Mean	Diff. from Grand Mean	CPV	Lab Mean	Diff. from Grand Mean	CPV
VV2MBN		136.70	0.65	0.41	132.00	-0.71	-0.62
W24ZNC		137.23	1.18	0.74	131.71	-1.00	-0.86
WAG3VY	*	140.53	4.48	2.82	135.43	2.72	2.36
WAGZ4A		133.47	-2.58	-1.62	132.81	0.10	0.09
WHR2PA		134.11	-1.94	-1.22	132.09	-0.62	-0.53
WLXHAY		136.67	0.61	0.39	133.67	0.96	0.83
WN2DT3		137.33	1.28	0.80	132.33	-0.38	-0.33
XLQWN4		138.20	2.15	1.35	134.73	2.02	1.75
YCEZJW	X	135.53	-0.52	-0.33	129.17	-3.54	-3.07
YQD79L		137.74	1.69	1.06	133.54	0.82	0.71
ZGPLRNU		138.24	2.19	1.38	132.64	-0.07	-0.06
ZWLMMF		136.72	0.67	0.42	134.21	1.50	1.30
ZZD4QT		134.16	-1.89	-1.19	131.07	-1.64	-1.42

Summary Statistics

Sample X13

Grand Means 136.05 ksi

Stnd Dev Btwn Labs 1.59 ksi

Sample X14

132.71 ksi

1.16 ksi

Samples X13, X14 : 3/8-16 x 2 1/2, 3/8-16 x 2 3/4

Statistics based on 55 of 60 reporting participants

Comments on Assigned Data Flags for Test #1201


236AUQ (X) - Data for sample X14 are high.

7GPJHQ (X) - Extreme data.

T2VPHH (X) - Inconsistent in testing between samples.

VH2JB4 (X) - Data for sample X14 are high. Inconsistent within the determinations of sample X14.

YCEZJW (X) - Data for sample X14 are low.



Fasteners and Metals Interlaboratory Testing Program

Analysis 1201

Fastener Wedge Tensile (10 degree)
ASTM F606

Cycle 1522

4th Qtr 2025


(WT)

SAMPLE X13

136.05 ksi

SAMPLE X14

132.71 ksi





Fasteners and Metals Interlaboratory Testing Program

Analysis 1201

Fastener Wedge Tensile (10 degree)

ASTM F606

Cycle 1522

4th Qtr 2025

(WT)

-End of Report-